Test Report

Applicant: Kindpouch Packing Co., Lld

Addrees: Room 119, No.165, Cuantal Rood, Nonchung Street. Dongguan City, Guangdong $22800

The following sample(s) and Information were submitted and ideotified by the applicant

Sample Name:	Pet Food Packaging Pooch
Product Description:	Pet Food Packaging Pooch (Flat bottorn/Quad seal pooch/Side gusent/Doypack Style, Food Grade, Laminated Film, High Berrier, Resealable Zipper, Largn Sizo Pet FeodPackaging Sack)
Model No.:	OP-FF003
Traderoack:	KindPack
Class:	Pet Food Peckaging
Manufacturer:	Kindpouch Packing Co., Lld
Manufacturer Address:	No.48, XianFeng Rood MingChen Town, Gaoming Diectrict, Feshan City, Guamgdong Province, China
Ongin of the Product(s):	China
Main Sutratunce:	PE
Sample Received Cote:	24-Jul-2028
Testing Period:	24-Jul-2036 to 28-Jul-2026
Testing Requirements:	Selected teet(s) as requested by cliunt
Test Method:	Plesse reler to nest page(s)
Test Results:	Please reler to neat page(s)
Summary of test results:	Please reler to neat page(s)

Authoriced signature

Fox Rong

Technical supervisor

Approved Signatory

Guanzhou Supreme Technology & Testing Service Co., Ltd.

Nute: This document cenool be reproduced exoept in fall, withsd urlor enibel oppoeval of the Comprng Any onaulbacized alteration, forgery is Glodlication of the ountool or appeanance of this document to unearful and offenders may be prosscoded to the beleot extend of the law Unicos otherwise sloted the vesulle shoses to this best report roler only to the sumpoing bottad Any demsnal to the corriect of test ngest, please proenes in 13 days after the report s sending act, it will hall be acrepted after this date.

Test Report

As requested by the applicant, for details refer to attechod page(s).

Test Requested	Conclusion
Regulation (EC) No 1938/2004 & Regulation (EU) No 10/2011 and its amenstment & AP(89)1	
Sensorial Examination Cdour and Teste Test	**PASS**
Visible Color migration	**PASS**
Specific Migration of 19 Heavy Metals	**PASS**
Conrall Migration	**PASS**
Specific migration for Primary Arcmatic Amines	**PASS**
Phthalates content	**PASS**
Polycyclic Aromatic Hydrocarbons (PAHs) Content	**PASS**
Specific Migration of Polycyclic Aromatic Hydrocurbons (PAHs)	**PASS**
Specific migration of hssene in olive oll	**PASS**
Specific migration of astene in olive oll	**PASS**
Bisphenol A(BPA) Content	**PASS**
Specific migration of Bispherol A(BPA)	**PASS**
Specific Migration of Formalochyde	**PASS**

Note: 1. The test resallt(s) are retated ocly to the test item(s) and hat part(s) appointed by client.

Note: This occumsed casted be reproduced escapt in to6. sethout price antiom agsocat of the Company Any unecthonord eltercism. Gogeny to faledcation of the connect os appeorance of the accumest is ontasetul and offendors may be prosessted to the fultect cotect of the fiec Lirtales uthenoise elexect the results cronect is this had report rolss only is the tsimpledul tested Any Gomonal to the contant of test repont please progoss to Hl days after the sopud's seeding act. It will ect for acrepted after this date.

Gonngzhou Supname Technology & Tasting Service Co，Ltd.

1E0. Reantina IT Fack, Scorn Tower, No 3 Maanehi Castro Man, Nardline Dnarad, Ouangzbusi Coy, Coangzhong Frovance China

Tvl. 003-39004143 For. GO-3S827/7 Finst wnee@envanting.com Websites http://trase.enclooding.com

Test Report

Test Result(s):

Test Sample / Part Description:

Sample /Part No.	Description(location)	Material (claimed by the client)
A1	Pet food bag	/
01	Silvery plastic (A1 pet food bag)	PE

Sensorial Examination Odour And Taste Test

Test Method: With reference to DIN10955:2024-01. No.of panelist: 6

Test Item(s)	Limit	Result
		A1
Test media	-	Distilled water
Test temperature	-	23℃
Test time	-	24hr(s)
Sensorial examination odour (Point scale)	2.5	0.0
Sensorial examination taste (Point scale)	2.5	0.0

Remarks:

Intensity scale (rounded at 0.5):
0 - no perceptible difference
1 - just perceptible difference
2 - slight difference
3 - marked difference
4 - strong difference

Note: This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Any objection to the content of test report, please propose in 15 days after the report's sending out, it will not be accepted after this date.

Visible Color migration

Test Method: AP(89)1

Test Item(s)	Test Condition	Limit	Result
			01
Visible Color migration	3% Acetic acid 40℃, 2h	No color leach out	No color leach out

Note: This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Any omission to the content of test report, please propose in 15 days after the report's sending out, it will not be accepted after this date.

Test Report

Specific Migration of 19 Heavy Metals

Test Method:EN 13130-1:2004, the analysis was performed by ICP-OES.

Test Item(s)	Test condition	Limit	Unit	Result		
				01		
				1st	2nd	3rd
Barium (Ba)	3% Acetic Acid 40℃, 2h	1	mg/kg	<0.1	<0.1	<0.1
Cobalt (Co)		0.05	mg/kg	<0.01	<0.01	<0.01
Copper (Cu)		5	mg/kg	<0.1	<0.1	<0.1
Iron (Fe)		48	mg/kg	<2	<2	<2
Lithium (Li)		0.6	mg/kg	<0.01	<0.01	<0.01
Zinc (Zn)		5	mg/kg	<0.1	<0.1	<0.1
Aluminum (Al)		1	mg/kg	<0.1	<0.1	<0.1
Manganese (Mn)		0.6	mg/kg	<0.01	<0.01	<0.01
Nickle (Ni)		0.02	mg/kg	<0.01	<0.01	<0.01
Lead (Pb)		0.01	mg/kg	<0.005	<0.005	<0.005
Cadmium (Cd)		0.002	mg/kg	<0.002	<0.002	<0.002
Arsenic (As)		0.01	mg/kg	<0.005	<0.005	<0.005
Mercury (Hg)		0.01	mg/kg	<0.005	<0.005	<0.005
Chromium (Cr)*		0.01	mg/kg	<0.005	<0.005	<0.005
Antimony (Sb)		0.04	mg/kg	<0.01	<0.01	<0.01
Europium (Eu)		-	mg/kg	<0.01	<0.01	<0.01
Gadolinium (Gd)		-	mg/kg	<0.01	<0.01	<0.01
Lanthanum (La)		-	mg/kg	<0.01	<0.01	<0.01
Terbium (Tb)		-	mg/kg	<0.01	<0.01	<0.01
Sum (Eu+Gd+La+Tb)		0.05	mg/kg	<0.05	<0.05	<0.05

Remarks:

1. mg/kg = miligram per kilogram = ppm
2. 1mg/kg = 0.0001%=1ppm
3. < = less than
4. "-" = Not Regulated
5. * * * = The detection limit of total chromium shall be 0.01mg kg.If there is evidence that hexavalent chromium is absent, the total chromium limit may be 3.6mg/kg.

Note: This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Any derivation to the content of test report, please propose in 15 days after the report's sending out, it will not be accepted after this date.

Guangzhou Supreme Technology & Testing Service Co., Ltd.

102, Nanjing IT Park, South Tower, No.2 Hannan Dadao Nan, Nanjing District, Guangzhou City, Guangdong Province, China

Tel: 020-38601143 Fax: 020-38601511 Email: service@xnotg.com Website: http://www.xnotg.com

Specific migration of Primary Aromatic Amines

Test Method: EN 13130-1:2004, analyzed by LC-MS/MS.

Test media: 3% Acetic Acid
Test temperature/ time: 40℃, 2hr(s)

	Test Item(s)	CAS No.	Limit	Unit	Result		
					01		
					1st	2nd	3rd
1	4-aminodiphenyl	92-67-1	0.002	mg/kg	<0.002	<0.002	<0.002
2	Benzidine	92-87-5	0.002	mg/kg	<0.002	<0.002	<0.002
3	4-chloro-o-toluidine	95-69-2	0.002	mg/kg	<0.002	<0.002	<0.002
4	2-naphthylamine	91-59-8	0.002	mg/kg	<0.002	<0.002	<0.002
5	o-aminoazotoluene	97-56-3	0.002	mg/kg	<0.002	<0.002	<0.002
6	2-amino-4-nitrotoluene	99-55-8	0.002	mg/kg	<0.002	<0.002	<0.002
7	p-chloroaniline	106-47-8	0.002	mg/kg	<0.002	<0.002	<0.002
8	2,4-diaminoanisole	615-05-4	0.002	mg/kg	<0.002	<0.002	<0.002
9	4,4'-diaminodiphenylmethane	101-77-9	0.002	mg/kg	<0.002	<0.002	<0.002
10	3,3-dimethoxybenzidine	119-90-4	0.002	mg/kg	<0.002	<0.002	<0.002
11	3,3'-dimethylbenzidine	119-93-7	0.002	mg/kg	<0.002	<0.002	<0.002
12	4,4'-Methylene-bis(2-methylaniline)	838-88-0	0.002	mg/kg	<0.002	<0.002	<0.002
13	p-cresidine	120-71-8	0.002	mg/kg	<0.002	<0.002	<0.002
14	4,4-methylene-bis-(2-chloroaniline)	101-14-4	0.002	mg/kg	<0.002	<0.002	<0.002
15	4,4'-oxydianiline	101-80-4	0.002	mg/kg	<0.002	<0.002	<0.002
16	4,4'-thiodianiline	139-65-1	0.002	mg/kg	<0.002	<0.002	<0.002
17	o-toluidine	95-53-4	0.002	mg/kg	<0.002	<0.002	<0.002
18	2,4-diaminotoluene	95-80-7	0.002	mg/kg	<0.002	<0.002	<0.002
19	2,4,5-trimethylaniline	137-17-7	0.002	mg/kg	<0.002	<0.002	<0.002
20	2-methoxyaniline	90-04-0	0.002	mg/kg	<0.002	<0.002	<0.002
21	4-aminoazobenzene	60-09-3	0.002	mg/kg	<0.002	<0.002	<0.002
22	Aniline	62-53-3	0.002	mg/kg	<0.002	<0.002	<0.002
23	3,3'-Dichlorobenzidine	91-94-1	0.002	mg/kg	<0.002	<0.002	<0.002

Remarks:

1. mg/kg = milligram per kilogram = ppm
2. 1mg/kg = 0.0001%=1ppm
3. < = less than

Note: This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Any demurral to the content of test report, please propose in 15 days after the report's sending out, it will not be accepted after this date.

Guangzhou Supreme Technology & Testing Service Co., Ltd.

103, NanSha IT Park, South Tower, No.2 HuanShi Dadao Nan, NanSha District, Guangzhou City, GuangDong Province China

Tel: 020-31004143 Fax: 020-31004617 Email: service@cosmetrg.com Website: http://www.xnotesting.com

Phthalates content

Test Method: EN 14372:2004 Clause 5.4.2, 3 6.3.2, analyzed by Gas Chromatography with Mass Spectrometry(GC-MS).

Test Item(s)	CAS No.	Limit	Unit	MDL	Result
					01
Dibutyl phthalate (DBP)	84-74-2	0.05	%	0.005	ND
Benzyl butyl phthalate (BBP)	85-68-7	0.1	%	0.005	ND
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	0.1	%	0.005	ND
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	0.1	%	0.01	ND
Di-isodecyl phthatlate (DIDP)	26761-40-0 68515-49-1	0.1	%	0.01	ND

Remarks:

1. % = Percentage by weight
2. 0.0001% = 1mg/kg = 1ppm
3. MDL = Method Detection Limit
4. ND = Not Detected (Less than MDL)

Note: The document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Any demurrer to the content of test report, please propose in 15 days after the report's sending out, it will not be accepted after this date.